

Interfacial Exchange Coupling in FeCo/MnGa Studied by X-ray Magnetic Circular Dichroism

Jun Okabayashi,^{1*} Kazuya Suzuki,² and Shigemi Mizukami²

¹Research Center for Spectrochemistry, University of Tokyo, Bunkyo-ku, Tokyo 113-0033, Japan

²WPI-Advanced Institute for Materials Research, Tohoku University, Sendai 980-8579, Japan

E-mail: jun@chem.s.u-tokyo.ac.jp

Magnetic ordered alloys have attracted significant attention for use as spintronics materials because they are highly likely to exhibit perpendicular magnetic anisotropy (PMA). Using the advantage that Mn_{3-8}Ga is a hard magnetic film, the deposition of other ferromagnetic materials on Mn_{3-8}Ga layers can be used to induce perpendicular exchange coupling through exchange interactions without the use of heavy metal elements. Ultra-thin $\text{Fe}_{1-x}\text{Co}_x$ layers deposited on Mn_{3-8}Ga couple ferromagnetically or antiferromagnetically, depending on their compositions [1]. Antiferromagnetic coupling has been demonstrated in high-Co-concentration regions, while low-Co-concentration regions have been shown to exhibit ferromagnetic coupling. However, the abruptness and element-specific magnetic properties at the interfaces between Mn_{3-8}Ga and $\text{Fe}_{1-x}\text{Co}_x$ layers must be clarified explicitly. Here, X-ray magnetic circular dichroism (XMCD) is employed to investigate the element-specific magnetic properties at an $\text{Fe}_{0.4}\text{Co}_{0.6}/\text{Mn}_{1.5}\text{Ga}$ interface. In particular, we discuss the interfacial coupling, which may be ferromagnetic or antiferromagnetic depending on the annealing of the samples.

The samples were prepared by magnetron sputtering on MgO substrates. On the 30-nm-thick MnGa, 1-nm FeCo were deposited at room temperature and capped by 2-nm MgO. We prepared two samples of as-grown and annealed at 350 °C after the growth. The X-ray absorption spectroscopy (XAS) and XMCD were performed at BL-7A in the Photon Factory (KEK). The total-electron-yield mode was adopted, and all measurements were performed at room temperature and the geometries were set to normal incidence configuration.

Figure 1 shows the polarization dependences of the XAS and XMCD results for the Mn, Fe, and Co L_{23} -edges after the annealing. By comparing these spectral line shapes with those in the as-grown case, it is evident that the XAS intensity ratios between Mn and FeCo are modulated, which suggests that the Fe and Co atoms diffuse chemically into the MnGa layer within the probing depth of approximately 5 nm. Opposite XMCD signs are observed in Fe and Co as shown in Fig. 1 because of the anti-parallel coupling between FeCo and MnGa layers. In the presentation, we discuss the interfacial element-specific magnetic properties depending on the annealing processes.

[1] Q. L. Ma et al., Phys. Rev. Lett. **112**, 157202 (2014).




Fig. 1. (a) XAS spectra of Mn, Fe, and Co L -edges in $\text{Fe}_{0.4}\text{Co}_{0.6}/\text{Mn}_{1.5}\text{Ga}$ 350 °C annealed sample. (b) XMCDs of Mn, Fe, and Co L -edges.