

Characteristics of bis-styrylbenzene derivatives with various electron-withdrawing groups

Hiroyuki Mochizuki and Masayuki Chikamatsu

Research center for photovoltaic
National Institute of Advanced Industrial Science and Technology
1-1-1 Higashi, Tsukuba, Ibaraki 305-8565, Japan
Phone: +81-29-861-5034 E-mail: h-mochizuki@aist.go.jp

Abstract

We synthesized 5 kinds of bis-styrylbenzene derivatives with various electron-withdrawing groups by the Horner-Wadsworth-Emmons reaction. The introduced electron-withdrawing groups were trifluoromethyl, trifluoromethoxy, trifluoromethylthio, cyano, and nitro moieties. The substituted position was both terminals of bis-styrylbenzene. The cyano moiety had a great effect on increase in the melting point of bis-styrylbenzene derivatives.

1. Introduction

Bis-styrylbenzene derivatives show high photo-physical and electronic properties due to their molecules conjugated extensively [1-3]. Their molecular planarity also allows good crystallinity, high melting point and high sublimation [4]. As characteristics of bis-styrylbenzene change markedly depending of substituent introduction, there have been reports on the bis-styrylbenzene derivatives with various substituents [5,6].

Trifluoromethyl moieties have been of interest because it is effective for improvement in the characteristics, such as increase in the electron-withdrawing ability, rise in the hydrophobicity, reduction in the melting point, etc [7-10]. We have evaluated photo-physical properties of 1,4-bis(4-trifluoromethylstyryl)benzene in detail, however, the effect of trifluoromethyl moiety on the photo-physical properties of bis-styrylbenzene was similar to that of methyl moiety [11].

Here, we report the introduction effects of various electron-withdrawing groups on properties of the bis-styrylbenzene derivatives.

2. Experiment

5 kinds of bis-styrylbenzene derivatives were synthesized by the Horner-Wadsworth-Emmons (HWE) reaction reported previously [2,12-15]. A 28 % methanol solution of sodium methoxide was added dropwise to a stirred mixture of *p*-bis(diethylphosphono)xylene and benzaldehyde with various electron-withdrawing groups in *N,N*-dimethylformamide (DMF) at rt. This mixture was then heated to 80 °C for 2 h. The reaction was then quenched with 2:1 DMF/H₂O and recrystallized from toluene affording the desired compounds: 1,4-bis(4-trifluoromethylstyryl)benzene (4CF3), 1,4-bis(4-trifluoromethoxystyryl)benzene (4OCF3), 1,4-bis(4-tri-

fluoromethylthiostyryl)benzene (4SCF3), 1,4-bis(4-cyanostyryl)benzene (4CN), 1,4-bis(4-nitrostyryl)benzene (4NO₂).






3. Results and discussion

The chemical structures and melting points of the prepared compounds are summarized in Table 1. Among the prepared 5 compounds, the melting points of 4CN was highest of 286 °C, even its molecular weight was lowest of 332. On the other hand, the melting point of 4SCF3 having the highest molecular weight was the lowest of 182 °C. The cyano moiety promoted the molecular stacking leading to high melting points.

References

- [1] H. Nakanotani, R. Kabe, M. Yahiro, T. Takenobu, Y. Iwasa, and C. Adachi, *Appl. Phys. Exp.* **1** (2008) 091801.
- [2] N. Mizoshita, Y. Goto, T. Tani, and S. Inagaki, *Adv. Funct. Mater.* **18** (2008) 3699.
- [3] R. Kabe, H. Nakanotani, T. Sakanoue, M. Yahiro, and C. Adachi, *Adv. Mater.* **21** (2009) 4034.
- [4] T. Yasuda, M. Saito, H. Nakamura, and T. Tsutsui, *Chem. Phys. Lett.* **452** (2008) 110.
- [5] J. Gierschner and S. Y. Park, *J. Mater. Chem. C* **1** (2013) 5818.
- [6] S. K. Park, I. Cho, J. Gierschner, J. H. Kim, J. H. Kim, J. E. Kwon, O. K. Kwon, D. R. Whang, J.-H. Park, B.-K. An, and S. Y. Park, *Angew. Chem. Int. Ed.* **55** (2016) 203.
- [7] H. Nakanotani and C. Adachi, *Appl. Phys. Lett.* **96** (2010) 053301.
- [8] S. Hotta and T. Yamao, *J. Mater. Chem.* **21** (2011) 1295.
- [9] S. K. Park, J. H. Kim, S.-J. Yoon, O. K. Kwon, B.-K. An, and S. Y. Park, *Chem. Mater.* **24** (2012) 3263.
- [10] S. K. Park, S. Varghese, J. H. Kim, S.-J. Yoon, O. K. Kwon, B.-K. An, J. Gierschner and S. Y. Park, *J. Am. Chem. Soc.* **135** (2013) 4757.
- [11] H. Mochizuki, Y. Sonoda, F. Sasaki, and R. Azumi, *Jpn. J. Appl. Phys.* **55** (2016) 022101.
- [12] B. E. Maryanoff and A. B. Reitz, *Chem. Rev.* **89** (1989) 863.
- [13] K. Sato, M. Higuchi, N. Iwata, T. C. Saido, and K. Sasamoto, *Eur. J. Med. Chem.* **39** (2004) 573.
- [14] D. P. Flaherty, S. M. Walsh, T. Kiyota, Y. Dong, T. Ikezu, and J. L. Vennerstrom, *J. Med. Chem.* **50** (2007) 4986.
- [15] I. Kikaš, B. Carlotti, I. Škorić, M. Šindler-Kulyka, U. Mazucato, and A. Spalletti, *J. Photoch. Photobio. A* **244** (2012) 38.

Table I The chemical structures and the melting point of prepared in the present study.

Abbreviated name	4CF3	4OCF3	4SCF3	4CN	4NO2
Chemical structure					
Melting point	274°C	242°C	182°C	286°C	286°C