ムルドカイト型酸化物 Mg₆MnO₈ ナノ粒子の合成と酸化触媒特性

(東工大フロンティア材料研) ○林 愛理・相原 健司・田村 高敏・鎌田 慶吾・原 亨和

Synthesis of Murdochite-type Oxide Mg₆MnO₈ Nanoparticles and the Catalytic Oxidation Properties (*Laboratory for Materials and Structures, Tokyo Institute of Technology*) ○Eri Hayashi, Takatoshi Tamura, Takeshi Aihara, Keigo Kamata, Michikazu Hara

Selective oxidation of hydrocarbons to oxygen-containing compounds is a key technology in the chemical industry. Molecular oxygen (O_2) economically and environmentally outperforms other oxidants. Therefore, catalytic oxidative C–H functionalization with O_2 as the sole oxidant has received much attention. The structure of Mg_6MnO_8 consisting of isolated tetravalent manganese species located in basic oxide MgO would be effective for the liquid phase oxidation due to the presence of both basicity and oxidizing ability. To date, Mg_6MnO_8 has been synthesized by sol–gel, impregnation, and solid-state methods; however, the surface areas are still low and the catalytic applications have been limited to gas-phase reactions. Herein, we report the synthesis and characterization of Mg_6MnO_8 nanoparticles with high surface area $(108 \text{ m}^2 \text{ g}^{-1})$ by the sol-gel method using malic acid, and their catalytic application to the selective oxidation of alkylarenes with O_2 . Mg_6MnO_8 nanoparticles exhibited much higher catalytic activity for the oxidation of fluorene than other manganese oxides.

Keywords: High Surface Area; Selective Oxidation; Murdochite-type Oxide

選択酸化反応は、C-H 結合を活性化し炭化水素 原料を工業的に有用な含酸素化合物に変換する 重要な反応であり、分子状酸素(O2)は、資源的 に豊富、低環境負荷などの利点を有する最も理 想的な酸化剤である。そのため、O2のみを酸化 剤とし選択酸化反応を高効率かつ温和な条件で 進行させることは重要である。ムルドカイト型 酸化物 Mg₆MnO₈ はマンガン 4 価が塩基性固体 MgO 中に孤立して存在しており、塩基性と酸化 能を併せもつことから液相酸化反応への応用が 期待される。これまでに様々な合成法が報告さ れているが、低表面積かつ応用例は気相反応の みとなっている。本研究では、リンゴ酸を用い たゾルゲル法による高表面積 Mg6MnO8の合成・ キャラクタリゼーションと種々の基質の酸素酸 化反応への触媒応用について検討を行った。合 成した Mg₆MnO₈の XRD パターンは、ムルドカ




Figure 1. Structure of cubic Mg₆MnO₈ and XRD patterns for Mg₆MnO₈ (upper) and cubic Mg₆MnO₈ (JCPDS 01-073-2157, lower).

イト型構造と良い一致を示した(Figure 1)。比表面積は $108 \text{ m}^2 \text{ g}^{-1}$ であり、これまでの報告値($2-15 \text{ m}^2 \text{ g}^{-1}$)よりも 7 倍以上大きな値であった。種々のマンガン酸化物を触媒とし、フルオレンの酸化反応により活性評価を行ったところ、 Mg_6MnO_8 は他のマンガン酸化物よりも高い活性を示した。本講演では Mg_6MnO_8 の基質適用性や反応メカニズムについても議論する。

1) E. Hayashi, T. Tamura, T. Aihara, K. Kamata, M. Hara, ACS Appl. Mater. Interfaces in revision.