イミン結合を有する共有結合性有機構造体の新規合成

(東理大理 ¹・東理大院理 ²) ○馬渕 春菜 ¹・金子 凌 ²・関根 大修 ²・Saikat Das ^{1,2}・川 脇 徳久 ^{1,2}・根岸 雄一 ^{1,2}

Synthesis of Novel Imine-linked Covalent Organic Framework (¹Undergraduate School of Science, Tokyo University of Science, ²Graduate School of Science, Tokyo University of Science) O Haruna Mabuchi, ¹ Ryo Kaneko, ² Taishu Sekine, ² Saikat Das, ^{1,2} Tokuhisa Kawawaki, ^{1,2} Yuichi Negishi ^{1,2}

Covalent organic frameworks (COFs) are crystalline porous materials composed of covalent bonds of light elements. COFs have applications in selective gas storage, catalysis, and membranes for wastewater treatment and dye separation due to their light weight, high thermal and chemical stability, and large specific surface area. The introduction of strong chemical bonds, such as imine bonds, has attracted much attention as a method to synthesize COFs with high stability. In this research, we synthesized COFs with a novel structure consisting of imine bonds formed by condensation of a compound with six aldehyde groups and four amino groups by hydrothermal synthesis (Fig. 1). Comparison of the powder X-ray diffraction results and their simulations revealed the presence of AA stacking structure in the product (1) (Fig. 2). In addition, Brunauer-Emmet-Teller measurements revealed a surface area of 637.7 m²g⁻¹ and an average pore size of 5.89 Å for 1. These results indicate that 1 is a porous material and is expected to have a wide range of applications such as gas adsorption and catalysis. In this report, we will also discuss the functionality of 1 as a separation membrane for dyes.

Keywords: Covalent organic framework; COF; Porous material; Imine bond

共有結合性有機構造体(COFs)は、軽元素の共有 結合により構成される結晶性の多孔質材料である。 COFs は軽量性、熱・化学的安定性、及び比表面積の 高さなどの特徴から、選択的なガス貯蔵、触媒、廃水 処理や染料分離等への応用が期待される。ここで、 イミン結合のような強固な化学結合の導入は、安定 性の高い COFs を合成する手法として注目されてい る¹⁾。そこで本研究では、水熱合成法を用いて、2つ のリンカー (Hexa(4-formylphenyl)benzene 及び 5,10,15,20-Tetrakis(4-aminophenyl)porphine)を縮合す ることでイミン結合から構成される新規構造の COF 合成を試みた(Fig. 1)。得られた生成物(**1**)と想定 される COF 構造の粉末 X 線回折 (PXRD) の比較か ら、1 は AA スタッキング構造を有することが示唆 された (Fig. 2)。加えて、Brunauer-Emmet-Teller 測定 により、その表面積は 637.7 m²g-1 であることが明ら かとなった。これらの結果より、1 は多孔性材料であ り、ガス吸着や触媒などへの応用が期待される。発 表では、1 を染料の色素分離膜として用いた際の機 能性についても報告する。

1) J. Caro et al., Angew. Chem. Int. Ed., 2018, 57, 4083.




Fig. 2 実験値及び計算値のPXRDパ