

## Chemical leaching experiments on the highly REY-rich mud collected near the Minamitorishima Island.

TAKAYA, Yutaro<sup>1\*</sup> ; FUJINAGA, Koichiro<sup>2</sup> ; NAKAMURA, Kentaro<sup>3</sup> ; IIJIMA, Koichi<sup>1</sup> ; KATO, Yasuhiro<sup>2</sup>

<sup>1</sup>JAMSTEC, <sup>2</sup>FRCER, Univ. of Tokyo, <sup>3</sup>Sys. Innovation, Univ. of Tokyo

Since the discovery of rare earths and yttrium (REY)-rich mud distributed widely on a deep seafloor in the Pacific Ocean (Kato et al., 2011), it has received broad attention as a new resource for REY. More recently, during research cruise KR13-02 of R/V Kairei, extremely REY-enriched deep-sea mud containing more than 6,000 ppm total REY ( $\sum$ REY) was collected near Minamitorishima Island, northwestern Pacific Ocean. One of the key issues on the future development and utilization of the new deep-sea mineral resources (REY-rich mud) is to establish a procedure to extract REY from the mud. Kato et al. (2011) showed that chemical leaching is an effective means to extract REY from REY-rich mud. In this study, therefore, we conducted series of leaching experiments on highly REY-rich mud ( $\sum$ REY  $\approx$  3,500 ppm) collected near Minamitorishima Island to determine the optimum conditions of REY leaching. Our results showed that more than 95% and 80 % of  $\sum$ REY can be recovered by hydrochloric acid and sulfuric acid, respectively. REY recovery was at the highest under the conditions of the lower acid concentration (0.25-0.5 mol/L), shortest leaching time (- 5min), and room temperature (25 °C). These leaching conditions are strong advantages for the development of REY-rich mud.

Keywords: deep-sea mineral resources, REY-rich mud, chemical leaching